

Ouachita Baptist University

Scholarly Commons @ Ouachita

Scholars Day Conference

Virtual Scholars Day 2020

May 1st, 12:00 AM - 12:00 AM

Investigating the Presence of BPA in Infant Oral Hygiene Products Using Fluorescence Spectroscopy

Kaleigh Casada

Ouachita Baptist University

Sara Hubbard

Ouachita Baptist University

Follow this and additional works at: https://scholarlycommons.obu.edu/scholars_day_conference

 Part of the [Materials Chemistry Commons](#)

Casada, Kaleigh and Hubbard, Sara, "Investigating the Presence of BPA in Infant Oral Hygiene Products Using Fluorescence Spectroscopy" (2020). *Scholars Day Conference*. 6.

https://scholarlycommons.obu.edu/scholars_day_conference/2020/natural_sciences/6

This Poster is brought to you for free and open access by the Carl Goodson Honors Program at Scholarly Commons @ Ouachita. It has been accepted for inclusion in Scholars Day Conference by an authorized administrator of Scholarly Commons @ Ouachita. For more information, please contact mortensona@obu.edu.



Investigating the Presence of BPA in Infant Oral Hygiene Products Using

Fluorescence Spectroscopy

Kaleigh G. Casada and Sara E. Hubbard, Ph.D.


Ouachita Baptist University, Arkadelphia, AR, 71998



The Center For Advanced
Surface Engineering

Abstract:

- Bisphenol-A (BPA) is a chemical found in hard plastics.
- BPA is an endocrine disruptor that binds to estrogen receptors. This is linked to negative health effects such as cardiovascular diseases and developmental issues.
- Infants and young children are more at risk to these effects because their endocrine systems are not fully developed.
- For this project, toothbrushes were investigated to determine if they contained BPA.
- Toothbrushes were further studied to determine if the BPA was primarily located in the bristles or heads.
- BPA is a fluorescent compound with an excitation wavelength of 278 nm and an emission wavelength of 304 nm, so a FS-5 spectrofluorometer from Edinburgh Instruments was used to determine the presence of BPA in each sample.



Materials and Methods, Continued:

- The bristles were removed from the BPA-containing toothbrushes.
- The bristles and the head of each toothbrush were then placed separately into 100-mL solutions of 1:1 M/W and analyzed following the protocol described above.
- Values were compared to determine the location of BPA in the toothbrushes.

Results:

Figure 1

Fluorescence Excitation and Emission peaks from the calibration curve of BPA in 1:1 M/W




Figure 2

Fluorescence Emission Calibration Curve for BPA




Figure 3

Fluorescence Emission Intensities of Toothbrush H and Toothbrush B over time





Figure 4

Fluorescence Emission Intensities of Components of Toothbrush H over time



Conclusions:

- After reviewing the data it appeared as though toothbrushes F and H contained traces of BPA. Neither of these toothbrushes were labeled as BPA free.
- There did not appear to be a distinct difference between the other unlabeled toothbrushes (A, B, E, G) and the toothbrushes that were labeled BPA free (C and D).
- Based upon the toothbrush isolation data, it appeared that the bulk of the BPA was located in the bristles of the toothbrush.

Future Work:

- Perform additional comparisons on toothbrush bristles and heads to determine the location of BPA in the toothbrushes.
- Perform statistical analysis to improve the accuracy of the conclusions made.
- Extend the testing period to improve the results in order to discover the full amount of BPA in each toothbrush.

References:

- Huang, Y. Q. "Bisphenol A (BPA) in China: A Review of Sources, Environmental Levels, and Potential Human Health Impacts." *Egyptian Journal of Medical Human Genetics*, Elsevier, 19 May 2011
- Nordqvist, Christian. "Bisphenol A: Hazards and Sources." *Medical News Today*, MediLexicon International, 25 May 2017
- Ellahi, Mujtaba, and Mamoon Ur Rashid. "The Toxic Effects BPA on Fetuses, Infants, and Children | IntechOpen." *Intech Open*, 7 June 2017

Acknowledgements:

- Dr. J.D. Patterson Summer Research Program
- Ouachita Baptist University

Materials and Methods:

- A variety of children's toothbrushes, labeled A-H, were selected and tested for the presence of BPA.
- Each toothbrush was placed in 100 mL of a 1:1 methanol:water (M/W) solution at room temperature.
- A 5-mL aliquot of the solution was taken at time intervals ranging from 5 minutes to 1 week after the toothbrush was placed in the solution.
- Each sample was run in the spectrofluorometer in duplicate, where the emission and excitation intensities were reviewed and recorded to determine which toothbrushes contain BPA.

